Premium SBS Cap Sheet







ITEM CODE: 370C

Description:

RUBEROID® EnergyCap™ Mop Plus Granule FR membrane is a premium, heavy-duty, SBS-modified bitumen membrane. Its core is a strong, non-woven polyester mat that meets ASTM D6164 Type II specifications.

Uses:

RUBEROID® EnergyCap™ Mop Plus Granule FR membrane is suitable for cold-applied and hot mopping applied new roofing applications where long-term roof system performance is specified.

Advantages:

- Durability The heavyweight polyester mat core protects against splits and tears due to its pliability and elongation characteristics. Specially formulated modified asphalt gives RUBEROID® EnergyCap™ Mop Plus Granule FR membrane excellent performance.
- RUBEROID® EnergyCap™ Mop Plus Granule FR membrane is manufactured by GAF, a company with over 125 years in the roofing business.
- RUBEROID® EnergyCap™ Mop Plus Granule FR membrane is available in highly reflective white only.
- Product warranties and system guaranteesare available. Contact your local salesrepresentative for requirements, availability, and limitations.
 See warranties and guarantees on gaf.com for complete coverage and restrictions.

Product Application:



Hot-Asphalt



Storage and Handling:

To prevent damage, support rolls on end in an upright position and store in a clean dry location, covering as necessary to protect from environmental damage. Monitor environmental conditions during storage, handling, and application.

	ı
	⊢
	Н
	IS
	н
_	ш
	17
	3
	7
	В
	16
CDDCI	f
	C
4171	
COOL ROOF	ŀ
RATING COUNCIL ®	l٧
•	ln
	ľ
	I.

Rated Product ID #: 0676-0086a				
	Initial	Aged		
Solar Reflectance	0.74	0.66*		
Thermal Emittance	0.90	0.89*		
SRI	92	80*		
The ratings above are subject to CDDC rating program				

ne ratings above are subject to CRRC rating program onditions, requirements, and limitations. Visit cochuots.org or important information and disclaimers about CRRC rating onditions, requirements, and limitations.

CRRC Rapid Battings: These are interim laboratory-aged values that simulate weathered values. These values will be replaced with the measured three-year aged values upon completion of the weathering process. Ski values calculate using Rapid Rattings may change once the aged ratting replaces the interim ratting.

Physical Properties:

Property	Standard Minimum Value	GAF Value
Thickness, min. mm (mils), Grade G	130 (3.3)	160 (4.1)
Net mass/unit area, min. g/m2 (lbs/100 ft.²)	4,394 (90)	4,638 (95)
Bottom coating thickness, heat welding application products, min. mm (mils)	1.0 (40)	1.3 (50)
Peak load at -18 +/-2° C (0 +/-3.6° F), MD and CMD, min. before and after heat conditioning, kN/m (lbf/in.)	MD - 17.5 (100) CMD - 17.5 (100)	MD - 28.9 (165) CMD - 22.8 (130)
Elongation at -18 +/-2° C (0 +/-3.6° F), MD and CMD, min. at peak load, before and after heat conditioning, (%)	MD - 20.0 CMD - 20.0	MD - 55.0 CMD - 60.0
Peak load at 23 +/-2 $^{\circ}$ C (73.4 +/-3.6 $^{\circ}$ F), MD and CMD, min. before and after heat conditioning, kN/m (lbf/in.)	MD - 12.3 (70) CMD - 12.3 (70)	MD - 21.0 (120) CMD - 15.8 (90)
Elongation at 23 +/-2 $^{\circ}$ C (73.4 +/-3.6 $^{\circ}$ F), MD and CMD, min. at peak load, before and after heat conditioning, (%)	MD - 50.0 CMD - 50.0	MD - 70.0 CMD - 75.0
Ultimate elongation 23 +/-2° C (73.4 +/-3.6° F), MD and CMD, min. before and after heat conditioning, (%)	MD - 60.0 CMD - 60.0	MD - 85.0 CMD - 90.0
Tear strength at 23 +/-2 °C (73.4 +/-3.6° F), min. N (lbf)	311 (70)	645 (145)
Low-temperature flexibility, max. before and after heat conditioning, $^{\circ}$ C ($^{\circ}$ F)	-18 (0)	-18 (0)
Dimensional stability, max. (%)	1.00	0.55
Compound stability at 102° C (215° F)	No Failures	No Failures
Granule embedment, max. (g)	2.00	0.05

Note: Values stated are average values and subject to normal manufacturing variation. These values are not guaranteed and are provided solely as a guide.

Testing and Approvals:

- Classified by UL in accordance with ANSI/UL 790, including as component of Class A fire resistance rated roofing assemblies. Refer to UL Product iQ for specific assemblies.
- FM Approved refer to roofnav.com for approved assemblies.
- Miami-Dade County Product Control Approved.
- State of Florida Approved
- UL Evaluation Report UL ER1306-02.
- Texas Department of Insurance Report RC-49.
- Can be used to comply with 2022 Title 24, Part 6, Cool Roof requirements of the California Code of Regulations.
- Meets or exceeds ASTM D6164 Type II, Grade G
- For additional information, contact GAF Design Services at 1-877-423-7663 or designservices@gaf.com.









Product Specifications:

ASTM D6164 Type II, Grade G		
Roll Size*	107.3 ft. ² (10.0 m ²)	
Roll Length	32' 6" (10.0 m)	
Roll Width	39.625" (1.0 m)	
Roll Weight	105 lb. (47.6 kg)	
Roll Thickness	160 mils (4.1 mm)	
Rolls per Pallet	25	
Full Pallet Weight	2,675 lb. (1,213.4 kg)	
Reinforcement	Polyester	
Top Side Surfacing	Granule	
Bottom Side Surfacing	Sand	

* Roll size as reported represents actual membrane dimensions and does not calculate installation using side and end lap recommendations.



