

Sloped Polyiso with CGF Facers



Description:

EnergyGuard™ Ultra Tapered Polyiso Insulation is a sloped panel made of durable coated glass fiber facers (CGF) bonded to a core of polyisocyanurate foam.

Features and Benefits:

- Prevents ponding water when properly installed on a low-slope roof by providing slope via a series of both tapered and flat polyiso fill panels
- Versatile — approved in single-ply roofing systems, BUR, and modified bitumen with a variety of attachment methods to the deck: mechanically attached, fully adhered, loose laid, ballasted
- Highest R-value per inch of any rigid board insulation
- Easy to install — lightweight, easy to cut, easy to handle
- Increased mold resistance — meets the requirements of ASTM D3273 for resistance to mold⁵
- EnergyGuard™ Ultra Polyiso Insulation and EnergyGuard Ultra Tapered Polyiso Insulation achieve an ANSI/UL 790 Class A roofing fire resistance rating as a component of UL Classified roofing assemblies over combustible deck without the use of a gypsum board or slip sheet when installed at a minimum 3" (75mm) thickness. Refer to UL Product iQ for specific assemblies

Panel Characteristics:

Sizes: 4' x 4' (1.22 m x 1.22 m) – 4' x 8' (1.22 m x 2.44 m) available upon request

Thickness: ½" – 4½" (12.7 mm – 114.3 mm) in a single layer

Slope: ⅛" (1.6 mm), ⅙" (3.2 mm), ⅓" (4.8 mm), ¼" (6.35 mm), ⅜" (9.5 mm), ½" (12.7 mm)

Codes and Compliance:

- Meets the requirements of ASTM C1289 Type II, Class II, Grade 2 (20 PSI) or Grade 3 (25 PSI)
- FM Approved — refer to RoofNav.com for approved assemblies
- Classified by UL in accordance with ANSI/UL 1256 and 790. Refer to UL Product iQ for specific assemblies.
- UL Evaluation Report UL ER1306-03
- Miami-Dade County Product Control Approved
- State of Florida Approved
- Meets the requirements of CAN/ULC 704.1 Type 2, Class 3 or Type 3, Class 3¹
- UL (Canada) Evaluation Report ULC ER1306¹
- For additional information, contact GAF at 877-423-7663 or designservices@gaf.com

Tapered Design Team:

Our Tapered Design Team specialists are available within your region to assist you in all aspects of preplanning, design, and training. Reach out at tdg@GAF.com

Our services include:

- Conceptual design assistance
- Quote review and comparison
- Plan and spec review
- Alternate design recommendations
- Job startups, trainings, and presentations

Sustainability:

- Manufactured with EPA-compliant blowing agents containing no CFCs or HCFCs, zero ozone depletion potential (ODP) and negligible global warming potential (GWP)
- Potential LEED Credits for Polyiso Use
- UL GreenGuard Gold
- Environmental Product Declaration (EPD)



¹ GAF manufacturing facilities in UT and PA.



Visit gaf.com

We protect what matters most™



TYPICAL PHYSICAL PROPERTY DATA CHART ²

Property	Test Method	Values
Compressive Strength	ASTM D1621	Grade 2 – 20 psi min (138 kPa) or Grade 3 – 25 psi min (172 kPa)
Dimensional Stability Change (length + width) ³	ASTM D2126	< 2% linear change
Flexural Strength	ASTM C203	40 psi min (275 kPa)
Tensile Strength	ASTM C209	500 psf min (24 kPa)
Water Absorption (percent by volume)	ASTM C209	1.5% max
Water Vapor Permeance	ASTM E96, Procedure A	1.5 perm max (85.8 ng/Pa•s•m ²)
Service Temperature		-100° F to 250° F (-73.3° C to 121.1° C)
Flame Spread Index ⁴	ASTM E84	< 75 ²
Smoke Developed Index	ASTM E84	< 200 ²
Resistance to Mold ⁵	ASTM D3273	Pass (10)

² Foam Core

³ Stated dimensional stability tolerance; thickness shall not diminish by more than 4% max.

⁴ These numerical ratings are not intended to reflect hazards presented by these or any other material under actual fire conditions.

⁵ GAF warranties and guarantees do not provide coverage against mold or other biological growth. Refer to gaf.com for more information on warranty and guarantee coverage and restrictions.

TAPERED POLYISO PHYSICAL CHARACTERISTICS AND SHIPPING INFORMATION

Physical Characteristics				Shipping Information (4' x 4') (1.22 m x 1.22 m) 4'x8' (1.22 m x 2.44 m) available upon special request [†]				
Slope	Thickness (Inches/Millimeters)	Size*	Average Thickness (Inches/Millimeters)	Board Feet Per Panel	Boards/ Bundle	Boards/ Truck	Bundle/ Truck	Sq. Ft. Per Truck
1/16" (1.6 mm)	0.5 - 0.75 (12.7 - 19.1)	1	0.625 (15.9)	10	72	3,456	48	55,296 (5,137 sq. m)
	0.75 - 1.0 (19.1 - 25.4)	2	0.875 (22.2)	14	52	2,496	48	39,936 (3,710 sq. m)
	1.0 - 1.25 (25.4 - 31.8)	3	1.125 (28.6)	18	40	1,920	48	30,720 (2,854 sq. m)
	1.25 - 1.5 (31.8 - 38.1)	4	1.375 (34.9)	22	32	1,536	48	24,576 (2,283 sq. m)
	1.5 - 1.75 (38.1 - 44.5)	5	1.625 (41.3)	26	28	1,344	48	21,504 (1,998 sq. m)
	1.75 - 2.0 (44.5 - 51.0)	6	1.875 (47.6)	30	24	1,152	48	18,432 (1,712 sq. m)
	2.0 - 2.25 (51.0 - 57.2)	7	2.125 (54.0)	34	20	960	48	15,360 (1,427 sq. m)
	2.25 - 2.5 (57.2 - 64.0)	8	2.375 (60.3)	38	18	864	48	13,824 (1,284 sq. m)
1/8" (3.2 mm)	0.5 - 1.0 (12.7 - 25.4)	AA [†]	0.75 (19.1)	12	64	3,072	48	49,152 (4,566 sq. m)
	1.0 - 1.5 (25.4 - 38.1)	A [†]	1.25 (31.8)	20	38	1,824	48	29,184 (2,711 sq. m)
	1.5 - 2.0 (38.1 - 51.0)	B [†]	1.75 (44.5)	28	26	1,248	48	19,968 (1,855 sq. m)
	2.0 - 2.5 (51.0 - 64.0)	C [†]	2.25 (57.2)	36	20	960	48	15,360 (1,427 sq. m)
	2.5 - 3.0 (64.0 - 76.2)	D	2.75 (70.0)	44	16	768	48	12,288 (1,142 sq. m)
	3.0 - 3.5 (76.2 - 89.0)	E	3.25 (82.6)	52	14	672	48	10,752 (999 sq. m)
	3.5 - 4.0 (89.0 - 102.0)	F	3.75 (95.3)	60	12	576	48	9,216 (856 sq. m)
	4.0 - 4.5 (102.0 - 114.3)	FF	4.25 (108.0)	68	10	480	48	7,680 (713 sq. m)
3/16" (4.8 mm)	0.5 - 1.25 (12.7 - 31.8)	JJ	0.875 (22.2)	14	50	2,400	48	38,400 (3,567 sq. m)
	1.25 - 2 (31.8 - 51.0)	KK	1.625 (41.3)	26	26	1,248	48	19,968 (1,855 sq. m)
	2.0 - 2.75 (51.0 - 70.0)	LL	2.375 (60.3)	38	20	960	48	15,360 (1,427 sq. m)
	2.75 - 3.5 (70.0 - 89.0)	MM	3.125 (79.4)	50	15	720	48	11,520 (1,070 sq. m)
	1.0 - 1.75 (25.4 - 44.5)	J	1.375 (34.9)	22	34	1,632	48	26,112 (2,426 sq. m)
	1.75 - 2.5 (44.5 - 64.0)	K	2.125 (54.0)	34	22	1,056	48	16,896 (1,570 sq. m)
	2.5 - 3.25 (64.0 - 82.6)	L	2.875 (73.0)	46	16	768	48	12,288 (1,142 sq. m)
	3.25 - 4.0 (82.6 - 102.0)	M	3.625 (92.1)	58	12	576	48	9,216 (856 sq. m)
1/4" (6.35 mm)	0.5 - 1.5 (12.7 - 38.1)	X [†]	1.0 (25.4)	16	48	2,304	48	36,864 (3,425 sq. m)
	1.5 - 2.5 (38.1 - 64.0)	Y [†]	2.0 (51.0)	32	24	1,152	48	18,432 (1,712 sq. m)
	2.5 - 3.5 (64.0 - 89.0)	Z [†]	3.0 (76.2)	48	16	768	48	12,288 (1,142 sq. m)
	3.5 - 4.5 (89.0 - 114.3)	ZZ	4.0 (102.0)	64	12	576	48	9,216 (856 sq. m)
	1.0 - 2.0 (25.4 - 51.0)	G	1.5 (38.1)	24	32	1,536	48	24,576 (2,283 sq. m)
	2.0 - 3.0 (51.0 - 76.2)	H	2.5 (64.0)	40	18	864	48	13,824 (1,284 sq. m)
	3.0 - 4.0 (76.2 - 102.0)	I	3.5 (89.0)	56	12	576	48	9,216 (856 sq. m)
3/8" (9.5 mm)	0.5 - 2.0 (12.7 - 51.0)	SS	1.25 (31.8)	20	38	1,824	48	29,184 (2,711 sq. m)
	2.0 - 3.5 (51.0 - 89.0)	TT	2.75 (69.9)	44	16	768	48	12,288 (1,142 sq. m)
	1.0 - 2.5 (25.4 - 64.0)	S	1.75 (44.5)	28	27	1,296	48	20,736 (1,926 sq. m)
1/2" (12.7 mm)	0.5 - 2.5 (12.7 - 64.0)	Q [†]	1.5 (38.1)	24	32	1,536	48	24,576 (2,283 sq. m)
	2.5 - 4.5 (64.0 - 114.3)	QQ	3.5 (89.0)	56	12	576	48	9,216 (856 sq. m)
	1.0 - 3.0 (25.4 - 76.2)	XX	2.0 (51.0)	32	22	1,056	48	16,896 (1,570 sq. m)

* Availability for these tapered panel systems may vary for each region.

[†] 4' x 8' tapered panels are made upon special request at all GAF Polyiso Manufacturing facilities in all EnergyGuard products. Certain run minimums will apply. The piece count per bundle remains the same as in a 4' x 4' bundle. The boards per truck and bundles per truck would be half the numbers reflected above for.



Visit gaf.com

We protect what matters most[™]

