





Description

Used to clean exposed or contaminated seams prior to heat welding to remove any residual soap and help revitalize aged membranes.

Application

- Do not use on "bag fresh" material that has been exposed for less than 12 hours unless it has been contaminated.
- Follow the guidance below for cleaning PVC:

Light Contamination — Membrane that has been exposed overnight or up to a few days to airborne debris, foot traffic, dew, or light precipitation can usually be cleaned with a white cloth moistened with EverGuard® PVC Membrane Conditioner. Be sure to wait for solvent to flash off prior to welding.

Dirt-Based Contamination — Membrane that is dirt encrusted will require the use of a low-residue cleaner, such as Formula 409®, and a mildly abrasive scrubbing pad to remove the dirt. This must be followed by cleaning with a white cloth moistened with EverGuard® PVC Membrane Conditioner. Be sure to wait for solvent to flash off prior to welding.



Membrane Conditioner

Exposure-Based Contamination — Membrane that is weathered or oxidized will require the use of a low-residue cleaner such as Formula 409® and a mildly abrasive scrubbing pad to remove the weathered/oxidized top surface layer. This must be followed by cleaning with a white cloth moistened with EverGuard® PVC Membrane Conditioner. Unexposed membrane left in inventory for a year or more may need to be cleaned as instructed above. Be sure to wait for solvent to flash off prior to welding.

SPECIFICATIONS	
Can size:	1 gallon
Cans per carton:	4
Weight per case:	33 lb. (14.96 kg)
Cases per pallet:	48
Product SKU	85H1

Quality You Can Trust...From North America's Largest Roofing Manufacturer!™