

# TPO and PVC One-Part Pourable



## Description:

EverGuard® One-Part Pourable Sealant is a one-part, moisture-cure, self-levelling sealant designed for use in sealant pockets on single-ply roof systems. Since moisture-cure sealants cure with moisture in the air, it is suitable for application in damp and cold climates, as well as in dry climates. EverGuard® One-Part Pourable Sealant is formulated without solvents, contains no isocyanates, and will not shrink upon curing. It does not “outgas” or bubble on damp surfaces. EverGuard® One-Part Pourable Sealant is elastomeric and has excellent adhesion to most roofing materials and penetrations. It has a low durometer, which accommodates greater movement in penetration seals.

## Advantages:

- Formulated without solvents — less than 25 g/L VOC
- 100% solids by volume — will not shrink
- No outgassing on damp surfaces
- Self-levelling provides a smooth, professional finished look
- UV stable
- 20-minute skinover time at 70°F (22°C) and 50% relative humidity.
- Typically paintable within 24 hours. High humidity or cold temperatures may slow dry time.
- No special tools or mixing required
- Application at temperatures as low as 30°F (-1°C)

## Product Information:

### LEED® 4.1 BD+C: New Construction:

- Contributes to Low-Emitting Materials Credit

### VOC Content:

- Less than 25 grams/liter ASTM D2369 EPA Method 24 (tested at 240°F [115°C])

## Uses:

EverGuard® One-Part Pourable Sealant is designed for use with the EverGuard® Pourable Sealer Pocket on new and existing TPO, PVC, and PVC KEE roofs to seal irregular penetrations, such as metal frames, wires, and pipes.

Note: EverGuard® TPO Primer is required to prime the TPO surface before use. No primer is necessary for PVC or PVC KEE.

## VOC Compliance:

- Meets requirements of OTC rule for sealants and caulks
- Meets requirements of California's SCAQMD rule, the most stringent in the state

### Typical Properties

VOC (max)	<25 grams/liter
Service Temperature	-40°F (-40°C) to 200°F (93.3°C)
Full Cure	Rate of cure is dependent on atmospheric conditions. Curing proceeds at a rate of ¼" (6.35 mm) a week at 70°F (22°C) and 50% relative humidity. Lower temperature and humidity will slow the rate of cure. Higher temperature and humidity will accelerate rate of cure. Depths of more than 2" (51 mm) will cure through in 2 to 3 months.
Skin Time	Approximately 20 minutes at 70°F (22°C) and 50% relative humidity.
Shrinkage	0%
Tensile Strength	146 lbf (217 kg/m)
Elongation	300% ± 25%
Density	8.9 ± .2 lb. per gallon (1.068 g/ml)



Visit [gaf.com](http://gaf.com)

For additional information, contact GAF Design Services at 1-877-423-7663 or [designservices@gaf.com](mailto:designservices@gaf.com)

We protect what matters most™



EverGuard®  
**GAF One-Part**  
Pourable Sealant

## Application Instructions:

Surface should be clean, dry, and free of any loose materials. Remove all previously applied caulk, mastic, cement, and other contaminants from penetrations with a cleaner. All roof deck voids are to be filled with FlexSeal™ Sealant. Prime all surfaces (except EverGuard® PVC or EverGuard® PVC KEE) with EverGuard® TPO Primer. Allow primer to dry prior to applying EverGuard® One-Part Pourable Sealant. Fill the EverGuard® Pourable Sealer Pocket with EverGuard® One-Part Pourable Sealant to the top of the pocket, ensuring that all voids are filled. See GAF's published application and specifications manual for complete details.

## Application Temperature:

EverGuard® One-Part Pourable Sealant can be applied at temperatures as low as 30°F (-1°C). In these colder temperatures, it is recommended to keep the material stored inside or in a truck before using.

## Clean-up:

Wet adhesive can be removed using a solvent, such as alcohol. Cured EverGuard® One-Part Pourable Sealant can be removed by abrading or scraping the substrate.

## Cure Time:

EverGuard® One-Part Pourable Sealant is a moisture-cure sealant. Rate of cure is dependent on atmospheric conditions. Curing proceeds at a rate of ¼" (6 mm) a week at 70°F (22°C) and 50% relative humidity. Lower temperature and humidity will slow the rate of cure. Higher temperature and humidity will accelerate rate of cure. Depths of more than 2" (51 mm) will cure through in 2 to 3 months.

## Packaging:


- 0.53 gallon (2 L) pouch
- 4 pouches/case
- 48 cases/pallet
- Color: White Storage
- Recommended storage is between 40°F–90°F (4°C–32.2°C). Store unopened containers in a cool, dry area. Protect unopened containers from water, heat, and direct sunlight. Although EverGuard® One-Part Pourable Sealant will not freeze, it is recommended to store indoors before using to ensure easy gunning and levelling.

## Shelf Life:

One year from date of manufacture when stored in recommended conditions. Elevated temperature and high relative humidity may significantly reduce shelf life.

## Precautions:

- Do not apply at temperatures below 30°F (-1°C).
- Do not use on TPO without EverGuard® TPO Primer.
- Do not use on Hypalon® membranes.
- Do not install if rain is anticipated within four hours.
- Do not use in areas subject to continuous water immersion.
- Do not use in areas where prolonged chemical exposure is anticipated.
- Do not prime bonding surfaces with asphalt primer.
- Use GAF FlexSeal™ Caulk Grade Sealant as a "night sealant" around the base of the penetration. Do not use petroleum-based solvents, such as mineral spirits, for cleaning purposes.
- Maintain sealant at room temperature before applying to ensure easy pouring and levelling.
- Test and evaluate to ensure adequate adhesion.
- Dry all visible and standing water prior to applying sealant.



Visit [gaf.com](https://www.gaf.com)

We protect what matters most™

