



SureBond Primer – Data Sheet

PRODUCT DESCRIPTION

GAF SureBond Primer is a water-based acrylic primer used for sealing masonry and chalky surfaces.

APPROVED SUBSTRATES

Masonry (brick, block, stucco, and concrete) and chalky coated surfaces.

PACKAGING SIZES

2 gallon (7.6 liter) bucket
5 gallon (19 liter) pail

STORAGE & SHELF LIFE

PRODUCT STORAGE TEMPERATURE: 50°F – 90°F (10°C and 32°C). Do not open containers until ready to use the material. Do NOT allow the product to freeze.

SHELF LIFE: 18 months if unopened containers, if stored properly.

PHYSICAL PROPERTIES¹

Solids by Weight	25% [ASTM D1644]
Solids by Volume	23% [ASTM D2697]
Density	8.5 lbs/gal
VOC	<200 g/L

1. Values are approximate and subject to normal manufacturing variations. These values are not guaranteed and are provided solely as a guide.

APPLICATION INSTRUCTIONS

SURFACE PREPARATION: Clean and prepare surfaces by removing all loose and flaking particles, grease and laitance with the use of a stiff bristle push broom or power washing. Do not allow water to infiltrate the substrate during washing. Additional drying time may be required after the cleaning process. New concrete should be allowed to surface dry for at least 28 days before applying GAF SureBond Primer.

MIXING: Mix uniformly for 3 minutes prior to use. Do NOT attempt to thin or self-tint.

APPLICATION: Apply GAF SureBond Primer by brush or roller at the rates specified below. Apply evenly at a rate of 0.25 – <0.5 gal./100 ft² (1.02 – <2.04 L/10 m²) per coat.

SUBSTRATE	COVERAGE RATE
Coated Brick	0.33 gal/100 ft ² (1.34 L/10 m ²)
Stucco	0.4 gal/100 ft ² (1.63 L/10 m ²)
Painted Surface	0.25 gal/100 ft ² (1.02 L/10 m ²)
Block	0.4 gal/100 ft ² (1.63 L/10 m ²)
Split-Faced Block	<0.5 gal/100 ft ² (<2.04L/10 m ²)
COVERAGE: may vary due to porosity of substrate. The average surface will use 0.4 – 0.25 gal/100 ft ² . (1.63 - 1.02 L/10 m ²)	

WARRANTY

Refer to applicable warranties and guarantees, available at gaf.com, for complete coverage and restrictions.

LIMITATIONS & PRECAUTIONS

APPLICATION AIR TEMPERATURE: Min. 50°F (10°C). Do NOT heat containers.

APPLICATION SURFACE TEMPERATURE: 50°F – 120°F (10°C – 48°C). Cool temperatures/high humidity may slow drying.

Do NOT apply if rain, dew, fog, heavy moisture, condensation, or freezing temperatures are in the 8 hour forecast to ensure proper cure.

Call GAF Technical Support Services for temperature ranges outside these limits.

SAFETY & HANDLING

For specific information regarding safe handling of this material please refer to the Safety Data Sheet (SDS)

CLEAN UP

Use water and soap to thoroughly flush equipment. If product has hardened, clean with solvent.

APPROVALS

State of Florida Approved (FBC)	FL620 and FL20663
Miami-Dade County NOA	20-0130.07 and 21-0105.10

For application questions, contact GAF Technical Support Services at **1-877-GAF-ROOF**

We protect what matters most™

