

# GAF

### Mineral Surface



**ITEM CODES:** 1 SQ ROLL - 3403 1.25 SQ ROLL - 3404

#### **Description:**

GAFGLAS® Mineral Surfaced Cap Sheet is an asphalt-coated glass fiber mat cap sheet surfaced with mineral granules.

**GAFGLAS®** 

Cap Sheet

#### Uses:

HA:

GAFGLAS® Mineral Surfaced Cap Sheet is used as the surfacing ply in the application of hot-applied built-up roofs and as a top ply in base flashing construction.

#### Advantages:

- Durability glass base helps resist the effects of moisture on the roof system.
- Protection granule surface protects against ultraviolet damage.
- Aesthetic attractive granule surface requires no additional coating.
- Product warranties and system guarantees are available. Contact your local sales representative for requirements, availability, and limitations. See warranties and guarantees on gaf.com for complete coverage and restrictions.

#### Product Application:



## Storage and Handling:

To prevent damage, support rolls on end in an upright position and store in a clean, dry location, covering as necessary to protect from environmental damage. Monitor environmental conditions during storage, handling, and application.

#### Testing and Approvals:

**lineral** Surfaced

- Classified by UL in accordance with ANSI/UL 790, including as component of Class A fire resistance-rated roofing assemblies. Refer to UL Product iQ for specific assemblies.
- FM Approved refer to roofnay.com for approved assemblies.
- Miami-Dade County Product Control Approved.
- State of Florida Approved.
- Texas Department of Insurance Report RC-49.
- Meets or exceeds ASTM D3909.
- For additional information, contact GAF Design Services at 1-877-423-7663 or designservices@gaf.com.





#### **Physical Properties:**

Property	Standard Minimum Value	GAF Value
Average mass per roll, min. lb. (kg) 3" (75-mm) selvage	39.0 (31.3)	40.6 (32.5)
Mass per unit area of granule-surfaced sheet, min. lb./100 ft.² (g/m²)	63.2 (3,085)	65.1 (3,207)
MD Breaking Strength, lbf/in. (kN/m) (ASTM D5147)	8.8 (50.0)	10.8 (95.9)
XMD/CD Breaking Strength, lbf/in. (kN/m)	7.7 (44.0)	7.9 (70.5)
Mass per unit area of desaturated glass felt, min. Ib./100 ft.² (g/m²)	1.70 (83)	1.75 (85)
Granule Embedment, max loss (g)	2.00	1.16
Moisture at time of manufacture (%)	1.0	≤ 1.0
Mass per unit area of mineral matter passing a 3.35 mm (No. 6) sieve and retained on a 212 $\mu m$ (No. 70) sieve, min. (lb./100 ft.² (g/m²)	24 (1,170)	25 (1,221)
Tear Resistance lbf (N)	55 (244)	61 (271)

Note: Values stated are average values and subject to normal manufacturing variation. These values are not guaranteed and are provided solely as a guide.



Visit gaf.com

Cold Applied

We protect what matters most

Product Specifications:

ASTM	D3909

, (entr 2070)		
106.6 fl. <sup>2</sup> (10.0 m <sup>2</sup> ) 132.9 (12.3 m <sup>2</sup> )		
32' 6" (10.0 m) 40' 6" (12.3 m)		
39.375" (1.0 m)		
68 lb. (30.4 kg) 87.5 (39.7 kg)		
105 mils 95 mils		
30 30		
2,090 lb. (948 kg) 2,675 lb. (1,213 kg)		
Glass-Fiber		

- \* Roll size as reported represents actual membrane dimensions and does not calculate installation using side and end lap recommendations.